1 # SEMICONDUCTOR LASER ARRAY DEVICE EMPLOYING MODULATION
2 # DOPED QUANTUM WELL STRUCTURES
3
4 ## BACKGROUND OF THE INVENTION
5
6 ### 1. Field of the Invention
7
8     This invention relates broadly to field of semiconductor devices (and associated
9 fabrication methodology) and, in particular, to semiconductor devices (and associated
10 fabrication methodology) that utilize modulation doped quantum well heterojunctions to
11 realize multiple-wavelength laser (detector) arrays.
12
13 ### 2. State of the Art
14
15     Multi-wavelength laser arrays are attractive light sources for wavelength division
16 multiplexing communication systems. Typically, such laser arrays are realized by
17 vertical cavity surface-emitting lasers (VCSELs) fabricated into 2-D arrays. The
18 emission wavelength of a VCSEL is usually determined during epitaxial growth by layer
19 thicknesses.
20
21     In Wipiejewski et al., "Vertical-Cavity Surface-Emitting Laser Diodes with Post-
22 Growth Wavelength Adjustment", a vertical-cavity laser is provided that includes an
23 active layer sandwiched between a bottom Distributed Bragg Reflector (DBR) mirror and
24 a top DBR mirror. The active layer consists of three InGaAs quantum wells with GaAs
25 barriers and AlGaAs cladding layers. On top of the top DBR mirror is formed a GaAs
26 tuning layer, an $SiO_2$ layer and reflective Au top layer. Etching of the GaAs tuning layer
27 after epitaxial growth and before metal deposition sets the laser cavity length and
28 corresponding emission wavelength of the vertical cavity laser. The emission
29 wavelengths of individual lasers in a 2-D array VCSEL are controlled by adjusting the
30 thickness of the GaAs tuning layer by a controllable etching process (utilizing anodic
31 oxidation with in situ voltage monitoring and subsequent semiconductor oxide removal).

1

2        Although the vertical-cavity laser array of Wipiejewski et al. succeeds in

3    providing in situ adjustment of the emission wavelength of the individual laser elements

4    in a 2-D laser array, it has many disadvantages. For example, electrical contact is made

5    through the GaAs tuning layer. Because the depth of the GaAs tuning layer varies from

6    wavelength to wavelength, the threshold current of the devices of the array vary, which

7    makes it very difficult to control the devices of the array. In addition, it is difficult to

8    control the depth of the GaAs tuning layer when utilizing anodic etching as described,

9    thus making it difficult to manufacture the array. Finally, in many applications (such as

10    DWDM communication systems) there are significant cost advantages that arise by

11    monolithic integration of a laser array with supporting electronic circuitry (e.g., laser

12    drive circuitry), waveguides and/or other optoelectronic devices, and Wipiejewski et al.

13    does not provide a mechanism for accomplishing such integration.

14

15        Wavelength division multiplexing communication systems also require multi-

16    wavelength detection systems. Typically, such optical detection systems are realized by

17    an optical demultiplexer (e.g., a fiber bragg grating or thin film optical filter) that

18    separates the desired wavelength components in the incident light signal. The

19    wavelength components are directed to a photodetector array. This approach is costly

20    due to the high costs of packaging the optical demultiplexer with the photodetector array.

21

22        The state of the art in wavelength demultiplexing is performed by an element

23    called the array wavelength grating (AWG). This is an element laid out in the plane of an

24    integrated circuit that routes all wavelengths by waveguide into a free space region

25    (parallel to the chip surface) from one side with a particular shape such that destructive

26    interference takes place on the exit side and each wavelength is thereby guided to a

27    unique output port. This arrangement is consumptive of real estate on the integrated

28    circuit and is limited in wavelength resolution (i.e., the shape of the exit side will only

29    allow a certain wavelength interval which is equivalent to the Q of an optically resonant

30    filter).

31

1    Thus, there remains a need in the art for improved multi-wavelength

2    laser/detection mechanisms in addition to multi-wavelength laser/detection mechanisms

3    that are suitable for monolithic integration with a broad range of electronic circuitry (such

4    as FETs and bipolar type transistors, logic, etc), waveguides and other optoelectronic

5    devices.

6

7                    SUMMARY OF THE INVENTION

8

9    It is therefore an object of the invention to provide multi-wavelength

10   laser/detection mechanisms which may be integrated with a broad range of devices such

11   as optical emitters, optical detectors, optical modulators, optical amplifiers, transistors,

12   and optical waveguides.

13

14   It is another object of the invention to provide multi-wavelength light processing

15   devices (multi-wavelength optical emitters, multi-wavelength optical detectors, multi-

16   wavelength optical modulators, multi-wavelength optical amplifiers) that have improved

17   ease of integration with a broad range of devices such as transistors, optical waveguides,

18   and optical interconnects.

19

20   It is a further object of the invention to provide multi-wavelength light processing

21   devices (multi-wavelength optical emitters, multi-wavelength optical detectors, multi-

22   wavelength optical modulators, multi-wavelength optical amplifiers) utilizing an array of

23   thyristor devices formed from a multilayer growth structure that can also be used to build

24   a broad range of devices such transistors, optical waveguide devices and optical

25   interconnects.

26

27   It is an additional object of the invention to provide a multilayer growth structure

28   which can be used to realize on a single integrated circuit chip a multi-wavelength light

29   processing device (multi-wavelength optical emitter, multi-wavelength optical detector,

30   multi-wavelength optical modulator, multi-wavelength optical amplifier) and a wide

1 range of optoelectronic devices (including FET devices, bipolar transistor devices,

2 waveguide devices and optical interconnect devices).

3

4 Another object of the invention is to provide fabrication methodology that

5 operates on a multilayer layer structure to produce an array of thyristor devices that can

6 be adapted to operate as a multi-wavelength light processing device (multi-wavelength

7 optical emitter, multi-wavelength optical detector, multi-wavelength optical modulator,

8 multi-wavelength optical amplifier).

9

10 In accord with these objects, which will be discussed in detail below, an

11 optoelectronic integrated circuit (and corresponding fabrication methodology) includes a

12 substrate, a multilayer structure formed on the substrate, and an array of thyristor devices

13 and corresponding resonant cavities formed in the multilayer structure. The resonant

14 cavities, which are adapted to process different wavelengths of light, are formed by

15 selectively removing portions of said multilayer structure to provide the resonant cavities

16 with different vertical dimensions that correspond to the different wavelengths.

17 Preferably, that portion of the multilayer structure that is selectively removed to provide

18 the multiple wavelengths includes a periodic substructure formed by repeating pairs of an

19 undoped spacer layer and an undoped etch stop layer. The multilayer structure may be

20 formed from group III-V materials. In this case, the undoped spacer layer and undoped

21 etch stop layer of the periodic substructure preferably comprises undoped GaAs and

22 undoped AlAs, respectively. The undoped AlAs functions as an etch stop during etching

23 by a chlorine-based gas mixture that includes fluorine.

24

25 It will be appreciated that the array of multi-wavelength thyristor devices can be

26 used to realize devices that provide a variety of optoelectronic functions, such as an array

27 of thyristor-based lasers that emit light at different wavelengths and/or an array of

28 thyristor-based detectors that detect light at different wavelengths (e.g., for wavelength-

29 division-multiplexing applications). In addition, the array of multi-wavelength thyristor

30 devices is well suited for monolithic integration with a wide range of optoelectronic

1     devices (including FET devices, bipolar transistor devices, waveguide devices and optical

2     interconnect devices).

3

4         Additional objects and advantages of the invention will become apparent to those

5     skilled in the art upon reference to the detailed description taken in conjunction with the

6     provided figures.

7

8                   BRIEF DESCRIPTION OF THE DRAWINGS

9

10        FIG. 1 is a schematic showing a multilayer structure in accordance with the

11     present invention, and from which the multi-wavelength thyristor array and other

12     optoelectronic/electronic devices can be made in accordance with the present invention.

13

14        FIG. 2A is a schematic showing an exemplary multilayer structure having a seven

15     period spacer layer structure formed over the modulation-doped quantum well active

16     device structure of FIG. 1 in accordance with the present invention, and from which the

17     multi-wavelength thyristor array and other optoelectronic/electronic devices can be made

18     in accordance with the present invention.

19

20        FIG. 2B is a schematic showing an exemplary thyristor device of a multi-

21     wavelength thyristor array formed from the layer structure of FIG. 2A wherein three

22     periods of the original seven period spacer layer structure are removed via *in situ* etching

23     operations.

24

25        FIG. 2C is a schematic showing another exemplary thyristor device of a multi-

26     wavelength thyristor array formed from the layer structure of FIG. 2A wherein the

27     original seven period spacer layer structure is retained during *in situ* etching operations.

28

29        FIG. 3 is a schematic showing an exemplary multilayer structure made with group

30     III-V material in accordance with the present invention, and from which the multiple

1 wavelength thyristor array and other optoelectronic/electronic devices can be made in

2 accordance with the present invention.

3

4 FIGS. 4A and 4B, collectively, are a flow chart illustrating an exemplary

5 methodology of fabricating the multilayer structure of FIG. 3 to form the multiple

6 wavelength thyristor array in accordance with the present invention.

7

8 FIGS. 5A - 5E are plan views illustrating different steps during the fabrication

9 methodology of FIGS. 4A and 4B.

10

11 FIGS. 6A and 6B are schematic views showing the generalized construction of

12 two exemplary resonant cavity thyristor devices formed from the layer structure of FIG.

13 3.

14

15 FIG. 7A is a pictorial illustration of an exemplary configuration of a thyristor as a

16 laser.

17

18 FIG. 7B is a graph showing the current-voltage characteristics of the thyristor

19 device in the NON-Conducting/OFF state of operation and the Conducting/ON state of

20 operation, and the operational conditions that cause the thyristor device to switch

21 between the OFF state of operation and the ON state of operation.

22

23 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

24

25 The present invention builds upon novel device structures utilizing modulation-

26 doped quantum well (QW) heterojunctions that do not suffer from the problems

27 associated with the prior art PHEMT devices and prior art HBT devices. Such novel

28 device structures are described in detail in U.S. Patent 6,031,243; U.S. Patent Application

29 No. 09/556,285, filed on April 24, 2000; U.S. Patent Application No. 09/798,316 filed on

30 March 2, 2001; International Application No. PCT/US02/06802 filed on March 4, 2002;

31 U.S. Patent Application No. 08/949,504, filed on October 14, 1997, U.S. Patent

1    Application No. 10/200,967, filed on July 23,2002; U.S. Application No. 09/710,217,

2    filed on November 10,2000; U.S. Patent Application No. 60/376,238, filed on April 26,

3    2002; U.S. Patent Application No. 10/280,892, filed on October 25, 2002; U.S. Patent

4    Application No. 10/323,390, filed on December 19, 2002; U.S. Patent Application No.

5    10/323,513, filed on December 19, 2002; U.S. Patent Application No. 10/323,389, filed

6    on December 19, 2002; U.S. Patent Application No. 10/323,388, filed on December 19,

7    2002; U.S. Patent Application No. 10/340,942, filed on January 13, 2003; each of these

8    references herein incorporated by reference in its entirety.

9

10    Turning now to FIG. 1, a multi-layer sandwich structure in accordance with the

11   present invention, and from which devices of the present invention can be made, includes

12   a bottom dielectric distributed bragg reflector (DBR) mirror 12 formed on a substrate 10.

13   The bottom DBR mirror 12 typically is formed by depositing pairs of semiconductor or

14   dielectric materials with different refractive indices. When two materials with different

15   refractive indices are placed together to form a junction, light will be reflected at the

16   junction. The amount of light reflected at one such boundary is small. However, if

17   multiple junctions/layer pairs are stacked periodically with each layer having a quarter-

18   wave ($\lambda$/4n) optical thickness, the reflections from each of the boundaries will be added

19   in phase to produce a large amount of reflected light (e.g., a large reflection coefficient)

20   at the particular center wavelength $\lambda_D$. Deposited upon the bottom DBR mirror 12 is the

21   active device structure which logically consists of two HFET devices. The first of these is

22   a p-channel HFET device 11 (referred to herein as PHFET 11) comprising layers 14, 16,

23   18, 20 and 22. The PHFET device 11 which has one or more p-type modulation doped

24   QW channels and is positioned with the gate terminal on the lower side (i.e. on the

25   bottom DBR mirror 12) and the collector terminal on the upper side. The second of these

26   is an n-channel HFET device 13 (referred to herein as NHFET 13) comprising layers 22,

27   24, 26, 28, 30. The NHFET device 13 has one or more n-type modulation doped QW

28   channels and is positioned with the gate terminal on the top side and the collector

29   terminal on the lower side which is the collector of the p-channel device. Therefore a

30   non-inverted N-channel device is stacked upon an inverted p-channel device to form the

31   active device structure.

1

2      The active device layer structure begins with n-type ohmic contact layer(s) 14

3  which enables the formation of ohmic contacts thereto.  Deposited on layer 14 are one or

4  more n-type layer(s) 16.  Preferably, the doping of layer(s) 16 is such that it should not be

5  depleted in any range of operation of the device, i.e. the total doping in this layer should

6  exceed the total doping charge contained in the modulation doped layer of the p-type

7  modulation doped QW structure 20 described below.  This layer 16 also serves optically

8  as a small part of the lower waveguide cladding for optical devices realized in this

9  structure.  Note that a majority of the lower waveguide cladding is provided by the lower

10  DBR mirror 12 itself.  Deposited on layer 16 is an undoped spacer layer 18.  Layers 14,

11  16 and 18 serve electrically as part of the gate of the p-channel HFET 11.  In this

12  configuration, layer 14 achieves low contact resistance and layer 18 defines the

13  capacitance of the p-channel HFET 11 with respect to the p-type modulation doped QW

14  heterostructure 20.  Deposited on layer 18 is a p-type modulation doped QW structure 20

15  that defines one or more quantum wells (which may be formed from strained or

16  unstrained heterojunction materials).  Deposited on the p-type modulation doped QW

17  structure 20 is an undoped spacer layer 22, which forms the collector of the P-channel

18  HFET device 11.  All of the layers grown thus far form the P-channel HFET device 11

19  with the gate ohmic contact on the bottom.

20

21      Undoped spacer layer 22 also forms the collector region of the N-channel HFET

22  device 13.  Deposited on layer 22 is an n-type modulation doped QW structure 24 that

23  defines one or more quantum wells (which may be formed from strained or unstrained

24  heterojunction materials).  Deposited on the n-type modulation doped QW structure 24 is

25  an undoped spacer layer 26.  Deposited on layer 26 are one or more p-type layer(s) 28.

26  Preferably, the doping of layer(s) 28 is such that it should not be depleted in any range of

27  operation of the device, i.e. the total doping in this layer should exceed the total doping

28  charge contained in the modulation doped layer of the n-type modulation doped QW

29  structure 24 described above.  Deposited on layer 28 are one or more p-type ohmic

30  contact layer(s) 30 which enable the formation of ohmic contacts thereto.  In this

31  configuration, layer 30 achieves low contact resistance and layer 26 defines the

1   capacitance of the n-channel HFET 13 with respect to the n-type modulation doped QW

2   heterostructure 24. Layers 28 and 30 serve electrically as part of the gate of the n-

3   channel HFET 13.

4

5   Alternatively, the active device structure may be described as a pair of stacked

6   quantum-well-base bipolar transistors formed on the bottom DBR mirror 12. The first of

7   these is an n-type quantum-well-base bipolar transistor (comprising layers 14, 16, 18, 20

8   and 22) which has one or more p-type modulation doped quantum wells and is positioned

9   with the emitter terminal on the lower side (i.e. on the mirror as just described) and the

10  collector terminal on the upper side. The second of these is an n-type quantum-well-base

11  bipolar transistor comprising layers 22, 24, 26, 28, and 30. This n-type quantum-well-

12  base bipolar transistor has one or more n-type modulation doped quantum wells and is

13  positioned with the emitter terminal on the top side and the collector terminal on the

14  lower side (which is the collector of the p-type quantum-well-base bipolar transistor).

15  Therefore a non-inverted n-channel device is stacked upon an inverted p-channel device

16  to form the active device structure. In this configuration, the gate terminal of the p-

17  channel HFET device 11 corresponds to the emitter terminal of the p-type quantum-well-

18  base bipolar transistor, the p-type QW structure 20 corresponds to the base region of the

19  p-type quantum-well-base bipolar transistor, spacer layer 22 corresponds to the collector

20  region of both the p-type quantum-well-base bipolar transistor and the n-type quantum-

21  well-base bipolar transistor, the n-type QW structure 24 corresponds to the base region of

22  the n-type quantum-well-base bipolar transistor, and the gate terminal of the n-channel

23  HFET device 13 corresponds to the emitter electrode of the n-type quantum-well-base

24  bipolar transistor.

25

26  Deposited on the active device layer structure is a thin undoped etch stop layer 31

27  and number N of undoped multilayer structures arranged one on top of the other to form a

28  periodic structure. Each multilayer structure 32 (which forms a period of the periodic

29  structure) includes an undoped spacer layer 32a and a thin undoped etch stop layer 32b.

30  As described below in detail, the N multilayer structures are selectively etched away to

31  set the optical path length (and corresponding wavelength) of the resonant cavity thyristor

1   devices formed therein.  The thickness of the spacer layer 30a in each undoped multilayer

2   structure 30 determines the range of optical path lengths (and corresponding range of

3   wavelengths) for the resonant cavity thyristor devices.

4

5   Note that etch stop layer 31 and etch stop layer 32b of the periodic structure are

6   optional, but may be helpful.  More specifically, these layers serve as an etch stop when

7   selectively etching away portions of the N multilayer structures to thereby enable the

8   undoped spacer layers to be removed sequentially with greater accuracy and efficiency.

9

10   To form a resonant cavity device where light enters into and/or is emitted from

11   the device laterally (i.e., from a direction normal to the cross section of FIG. 1), a

12   diffraction grating and top dielectric mirror are formed over that portion of the periodic

13   multilayer structure which remains after selective etching of the periodic multilayer

14   structure.  For resonant cavity lasing devices, the diffraction grating performs the

15   function of diffracting light produced by the resonant cavity into light propagating

16   laterally in a waveguide which has the top dielectric mirror and bottom DBR mirror as

17   waveguide cladding layers.  For resonant cavity detecting devices, the diffraction grating

18   performs the function of diffracting incident light that is propagating in the lateral

19   direction into a vertical mode, where it is absorbed resonantly in the resonant cavity.

20

21   Alternatively, light may enter (and/or exit) the resonant cavity in a vertical

22   direction through an optical aperture (not shown) in the top surface (or bottom surface) of

23   the device.  In this case, the diffraction grating is omitted, and the top dielectric mirror

24   and bottom DBR mirror define a resonant cavity for the vertical emission (and/or

25   absorption) of light such that the device operates as a vertical cavity surface emitting

26   laser (detector).

27

28   The optical path length between the bottom DBR mirror and top dielectric mirror

29   preferably represents an integral number of 1/2 wavelengths at the designated

30   wavelength. This optical path length is controlled by selectively etching away portions of

1 the periodic multilayer structure prior to formation of the top dielectric mirror to thereby

2 enable this condition.

3

4    *Turning now to FIG. 2A, there is shown an exemplary epitaxial growth structure*

5 having a seven undoped multilayer structures (32-1, 32-2 ... 32-7) formed above the

6 active device structure (layers 14 through 30). The optical path length between the

7 bottom DBR mirror 12 and the etch stop layer 31 represents an integral number of 1/2

8 wavelengths at a first wavelength $\lambda_1$. The optical path length between the bottom DBR

9 mirror 12 and the etch stop layer 32b for the multilayer structure 32-1 represents an

10 integral number of 1/2 wavelengths at a second wavelength $\lambda_2$. The optical path length

11 between the bottom DBR mirror 12 and the etch stop layer 32b for the multilayer

12 structure 32-2 represents an integral number of 1/2 wavelengths at a third wavelength $\lambda_3$.

13 The optical path length between the bottom DBR mirror 12 and the etch stop layer 32b

14 for the multilayer structure 32-3 represents an integral number of 1/2 wavelengths at a

15 fourth wavelength $\lambda_4$. The optical path length between the bottom DBR mirror 12 and

16 the etch stop layer 32b for the multilayer structure 32-4 represents an integral number of

17 1/2 wavelengths at a fifth wavelength $\lambda_5$. *The optical path length between the bottom*

18 DBR mirror 12 and the etch stop layer 32b for the multilayer structure 32-5 represents an

19 integral number of 1/2 wavelengths at a sixth wavelength $\lambda_6$. The optical path length

20 between the bottom DBR mirror 12 and the etch stop layer 32b for the multilayer

21 structure 32-6 represents an integral number of 1/2 wavelengths at a seventh wavelength

22 $\lambda_7$. The optical path length between the bottom DBR mirror 12 and the etch stop layer

23 32b for the multilayer structure 32-7 represents an integral number of 1/2 wavelengths at

24 an eighth wavelength $\lambda_8$.

25

26    In this configuration, the optical path length (and corresponding wavelength) of

27 the resonant cavities formed from this epitaxial growth structure is controlled by

28 selectively etching away portions of the multilayer structures 32-1 ... 32-7 prior to

29 formation of the top dielectric mirror. More specifically, an optical path length

30 corresponding to the first wavelength $\lambda_1$ is obtained by etching away the seven multilayer

31 structures 32-7 through 32-1 (and removing the etch stop layer 31) over the active device

1    structure for the cavity; an optical path length corresponding to the second wavelength $\lambda_2$

2    is obtained by etching away the six multilayer structures 32-7 through 32-2 (and

3    removing the etch stop layer 32b for the multilayer structure 32-1) over the active device

4    *structure for the cavity; an optical path length corresponding to the third wavelength $\lambda_3$ is*

5    obtained by etching away the five multilayer structures 32-7 through 32-3 (and removing

6    the etch stop layer 32b for the multilayer structure 32-2) over the active device structure

7    for the cavity; an optical path length corresponding to the fourth wavelength $\lambda_4$ is

8    obtained by etching away the four multilayer structures 32-7 through 32-4 (and removing

9    the etch stop layer 32b for the multilayer structure 32-3) over the active device structure

10   for the cavity; an optical path length corresponding to the fifth wavelength $\lambda_5$ is obtained

11   by etching away the three multilayer structures 32-7 through 32-5 (and removing the etch

12   stop layer 32b for the multilayer structure 32-4) over the active device structure for the

13   cavity; an optical path length corresponding to the sixth wavelength $\lambda_6$ is obtained by

14   etching away the two multilayer structures 32-7 and 32-6 (and removing the etch stop

15   layer 32b for the multilayer structure 32-5) over the active device structure for the cavity;

16   an optical path length corresponding to the seventh wavelength $\lambda_7$ is obtained by etching

17   away the multilayer structure 32-7 (and removing the etch stop layer 32b for the

18   multilayer structure 32-6) over the active device structure for the cavity; and, an optical

19   path length corresponding to the eighth wavelength $\lambda_8$ is obtained by removing the etch

20   stop layer 32b for the multilayer structure 32-7 over the active device structure for the

21   cavity. After this etching process, the top dielectric mirror (and possibly a diffraction

22   grating) are formed above the resulting structure to form a plurality of resonant cavities

23   whose optical path lengths correspond to the desired wavelengths.

24

25          For example, FIG. 2B illustrates a thyristor device formed in conjunction with a

26   resonant cavity whose optical path length corresponds to the fifth wavelength $\lambda_5$; while

27   FIG. 2C illustrates a thyristor device formed in conjunction with a resonant cavity whose

28   optical path length corresponds to the eighth wavelength $\lambda_8$. In both devices, one or more

29   anode terminal electrodes (two shown as 36a and 36b) are operably coupled to the top p-

30   type ohmic contact layer, one or more n-channel injector terminal electrodes (two shown

31   as 38a, 38b) are operably coupled to the n-type QW structure 24, one or more p-channel

1    injector terminal electrodes (two shown as 38C, 38D) are operably coupled to the p-type

2    QW structure 20, and one or more cathode terminal electrodes (two shown as 40a, 40b)

3    are operably coupled to the n-type ohmic contact layer 14. In alternative embodiments,

4    *the p-channel injector terminals (38c, 38d) may be omitted. In such a configuration, the*

5    N-channel injector terminals (38a, 38b), which are coupled to the n-type inversion QW

6    structure 24 are used to control charge in such n-type inversion QW channel(s) as

7    described herein. In yet another alternative embodiment, the N-channel injector

8    terminals (38a, 38b) may be omitted. In such a configuration, the p-channel injector

9    terminals (38c, 38d), which are coupled to the p-type inversion QW structure 20 are used

10    to control charge in such p-type inversion QW channel(s) as described herein.

11

12    The epitaxial growth structures described above may be realized with a material

13    system based on group III-V materials (such as a GaAs/AlGaAs). Alternatively, strained

14    silicon heterostructures employing silicon-germanium (SiGe) layers may be used to

15    realize the multilayer structures described herein. FIG. 3 illustrates an exemplary

16    epitaxial growth structure utilizing group III-V materials for realizing the structure of

17    FIG. 1 and the optoelectrical/electrical/optical devices formed from this structure in

18    accordance with the present invention.

19

20    The structure of FIG. 3 can be made, for example, using known molecular beam

21    epitaxy (MBE) techniques. As shown, a first semiconductor layer 151 of AlAs and a

22    second semiconductor layer 152 of GaAs are alternately deposited (with preferably at

23    least seven pairs) upon a semi-insulating gallium arsenide substrate 149 in sequence to

24    form the bottom distributed bragg reflector (DBR) mirror 12. The number of AlAs layers

25    will preferably always be one greater than the number of GaAs layers so that the first and

26    last layers of the mirror are shown as layer 151. In the preferred embodiment the AlAs

27    layers 151 are subjected to high temperature steam oxidation to produce the compound

28    $Al_xO_y$ so that a mirror will be formed at the designed center wavelength. This center

29    wavelength is selected such that all of the resonant wavelengths for the various cavities of

30    the array will be subject to high reflectivity. Therefore the thicknesses of layers 151 and

31    152 in the mirror are chosen so that the final optical thickness of GaAs and $Al_xO_y$ are one

1    quarter wavelength of the center wavelength $\lambda_D$. Alternatively the mirrors could be

2    grown as alternating layers of one quarter wavelength thickness of GaAs and AlAs at the

3    designed wavelength so that the oxidation step is not used. In that case, many more pairs

4    are required (with typical numbers such as 22 pairs) to achieve the reflectivity needed for

5    efficient lasing.

6          Deposited upon the mirror is the active device structure which consists of two

7    HFET devices. The first of these is the p-channel HFET (PHFET) 11 (see Fig. 1), which

8    has one or more p-type modulation doped quantum wells and is positioned with the gate

9    terminal on the bottom (i.e. on the mirror 12 just described) and the collector terminal

10    above. The second of these is an n-channel HFET (NHFET) 13, which has one or more

11    n-type modulation doped quantum wells and is positioned with the gate terminal on top

12    and the collector terminal below. The collector region of the NHFET device 13 also

13    functions as the collector region of the PHFET device 11. However, the collector

14    terminal of the NHFET device 13 is a p-type contact to p-type quantum well(s) disposed

15    below (above) the collector region, while the collector terminal of the PHFET device 11

16    is a n-type contact to n-type quantum well(s) disposed above the collector region.

17    Therefore a non-inverted n-channel device is stacked upon an inverted p-channel device

18    to form the active device structure.

19

20          The active-device layer structure begins with layer 153 of N+ type GaAs that

21    enables the formation of ohmic contacts thereto (for example, when contacting to the

22    cathode terminal of a thyristor device, the gate terminal of an inverted p-channel HFET

23    device, the sub-collector terminal of an n-channel HFET device, or the emitter terminal

24    of a p-type quantum-well-base bipolar device). Layer 153 has a typical thickness of

25    1000-3000 Å and a typical n-type doping of $3.5 \times 10^{18}\,cm^{-3}$. The N+ doped GaAs layer

26    153 corresponds to the ohmic contact layer 14 of FIG. 1. Deposited on layer 153 is layer

27    154 of n-type $Al_{x1}Ga_{1-x1}As$ with a typical thickness of 500-3000 Å and a typical doping

28    of $1 \times 10^{17}\,cm^{-3}$. The parameter x1 is preferably in the range between 70% and 80% (for

29    example, on the order of 70%) for layer 154. This layer serves as part of the PHFET gate

30    and optically as a small part of the lower waveguide cladding of the device. Note that a

31    majority of the lower waveguide cladding for waves propagating in the guide formed by

1    the optically active region of the device is provided by the lower DBR mirror itself. The

2    lower DBR mirror causes the light to be guided partially as a dielectric waveguide and

3    partially as a mirror waveguide. Next are 4 layers (155a, 155b, 155c, and 155d) of

4    $Al_{x2}Ga_{1-x2}As$. These 4 layers (collectively, 155) have a total thickness about 380-500 Å

5    and where x2 is about 15%. The first layer 155a is about 60-80 Å thick and is doped N+

6    type in the form of delta doping. The second layer 155b is about 200-300 Å thick and is

7    undoped. The third layer 155c is about 80 Å thick and is doped P+ type in the form of

8    delta doping. The fourth layer 155d is about 20-30 Å thick and is undoped to form a

9    spacer layer. This layer forms the lower separate confinement heterostructure (SCH)

10   layer for the laser, amplifier and modulator devices. The n-type AlGaAs layer 154 and n-

11   type AlGaAs layer 155a correspond to the n-type layer(s) 16 of FIG. 1, and the undoped

12   AlGaAs layer 155b corresponds to the undoped spacer layer 18 of FIG. 1.

13

14        The next layers define the quantum well(s) that form the inversion channel(s)

15   during operation of the PHFET 11. For a strained quantum well, this includes a spacer

16   layer 156 of undoped GaAs that is about 10-25 Å thick and then combinations of a

17   quantum well layer 157 that is about 40-80 Å thick and a barrier layer 158 of undoped

18   GaAs. The quantum well layer 157 may be comprised of a range of compositions. In the

19   preferred embodiment, the quantum well is formed from an $In_{0.2}Ga_{0.8}AsN$ composition

20   with the nitrogen content varying from 0% to 5% depending upon the desired natural

21   emission frequency. Thus, for a natural emission frequency of $.98\mu m$, the nitrogen

22   content will be 0%; for a natural emission frequency of $1.3\mu m$, the nitrogen content will

23   be approximately 2%; and for a natural emission frequency of $1.5\mu m$, the nitrogen

24   content will be approximately 4-5%. The well barrier combination will typically be

25   repeated (for example, three times as shown), however single quantum well structures

26   may also be used. Unstrained quantum wells are also possible. Following the last barrier

27   of undoped GaAs is a layer 159 of undoped $Al_{x2}Ga_{1-x2}As$ which forms the collector of the

28   PHFET device 11 and is about $0.5\mu m$ in thickness. All of the layers grown thus far form

29   the PHFET device 11 with the gate contact on the bottom. The layers between the P+

30   AlGaAs layer 155c and the last undoped GaAs barrier layer 158 correspond to the p-type

1 modulation doped heterojunction QW structure 20 of FIG. 1. Undoped AlGaAs layer

2 159 corresponds to the undoped spacer layer 22 of FIG. 1.

3

4       Layer 159 also forms the collector region of the NHFET device 13. Deposited on

5 layer 159 are two layers (collectively 160) of undoped GaAs of about 200-250 Å total

6 thickness, which form the barrier of the first n-type quantum well. Layer 160 is thicker

7 than the normal barrier layer of about 100 Å because it accommodates the growth

8 interruption to change the growth temperature from 610° C (as required for optical

9 quality $Al_{x2}Ga_{1-x2}As$ layers) to about 530°C for the growth of InGaAs. Therefore layer

10 160 includes a single layer 160a of about 150 Å and a barrier layer 160b of about 100 Å.

11 The next layer 161 is the quantum well of $In_{0.2}Ga_{0.8}As$, which is undoped and about 40-

12 80 Å in thickness. It is noted that the n-type quantum well layer 161 need not be of the

13 same formulation as the p-type quantum well layer 157. The barrier layer 160b of 100 Å

14 and quantum well layer 161 may be repeated, e.g., three times. Then there is a barrier

15 layer 162 of about 10-30 Å of undoped GaAs which accommodates a growth interruption

16 and a change of growth temperature. Next there are four layers (collectively 163) of

17 $Al_{x2}Ga_{1-x2}As$ of about 300-500 Å total thickness. These four layers (163) include a

18 spacer layer 163a of undoped $Al_{x2}Ga_{1-x2}As$ that is about 20-30 Å thick, a modulation

19 doped layer 163b of N+ type doping of $Al_{x2}Ga_{1-x2}As$ (with doping about $3.5x10^{18}$ cm$^{-3}$)

20 that is about 80 Å thick, a spacer layer 163c of undoped $Al_{x2}Ga_{1-x2}As$ that is about 200-

21 300 Å thick, and a P+ type delta doped layer 163d of $Al_{x2}Ga_{1-x2}As$ (with doping about

22 $3.5x10^{18}$ cm$^{-3}$) that is about 60-80 Å in thickness. Layers 163b and 163d form the top

23 plate and bottom plate of a parallel plate capacitor which forms the field-effect input to

24 all active devices. The doping species for layer 163d is preferably carbon (C) to ensure

25 diffusive stability. In contrast to layer 163b which is always depleted, layer 163d should

26 never be totally depleted in operation. For the optoelectronic device operation, layer 163

27 is the upper SCH region. The layers between the undoped GaAs barrier layer 160a and

28 the N+ AlGaAs layer 163b correspond to the n-type modulation doped heterojunction

29 QW structure 24 of FIG. 1. Undoped AlGaAs layer 163c corresponds to the undoped

30 spacer layer 26 of FIG. 1.

31

1    One or more layers (collectively 164) of p-type $Al_{x1}Ga_{1-x1}As$ are deposited next to

2    form part of the upper waveguide cladding for the laser, amplifier and modulator devices.

3    Note that a majority of the upper waveguide cladding for waves propagating in the guide

4    formed by the optically active region of the device is provided by the upper dielectric

5    mirror itself. The upper dielectric mirror causes the light to be guided partially as a

6    dielectric waveguide and partially as a mirror waveguide. Preferably, layer 164 has a

7    thickness on the order of 500-1500 Å, and includes a first thin sublayer 164a that is 10-20

8    Å thick and has a P+ doping of $10^{19}$ cm$^{-3}$ and a second sublayer 164b that is 700 Å thick

9    and has a P doping of $1 \times 10^{17} - 5 \times 10^{17}$ cm$^{-3}$. The parameter x1 of layer 164 is preferably

10   about 70%. The p-type layers 163b, 164a, 164b correspond to the p-type layer(s) 28 of

11   FIG. 1.

12

13   Deposited next is an ohmic contact layer 165 (which may comprise a single layer

14   of GaAs or a combination of GaAs (165a) and InGaAs (165b) as shown). Layer 165 is

15   about 50-100 Å thick and is doped to a very high level of P+ type doping (about $1 \times 10^{20}$

16   cm$^{-3}$) to enable formation of ohmic contacts thereto (for example, when contacting to the

17   anode terminal of a thyristor device).

18

19   Alternatively, the active device structure may be described as a pair of stacked

20   quantum-well-base bipolar transistors formed on the bottom DBR mirror (layers

21   151/152). The first of these is an p-type quantum-well-base bipolar transistor

22   (comprising layers 153 through 159) which has one or more p-type modulation doped

23   quantum wells and is positioned with the emitter terminal on the lower side (i.e. on the

24   bottom mirror as just described) and the collector terminal on the upper side. The second

25   of these is an n-type quantum-well-base bipolar transistor (comprising layers 159 through

26   165b) which has one or more n-type modulation doped quantum wells and is positioned

27   with the emitter terminal on the top side and the collector terminal on the lower side

28   which is the collector of the p-type quantum-well-base bipolar transistor. Therefore a

29   non-inverted n-channel device is stacked upon an inverted p-channel device to form the

30   active device structure. In this configuration, the cathode terminals 40a, 40b of the

31   thyristor device corresponds to the emitter electrode of the p-type quantum-well-base

1  bipolar transistor, the p-type QW structure (layers 155c though 158) corresponds to the

2  base region of the p-type quantum-well-base bipolar transistor, spacer layer 159

3  corresponds to the collector region of both the p-type quantum-well-base bipolar

4  transistor and the n-type quantum-well-base bipolar transistor, the n-type QW structure

5  (layers 160a through 163b) corresponds to the base region of the n-type quantum-well-

6  base bipolar transistor, and the anode terminals 36a, 36b of the thyristor device

7  correspond to the emitter electrode of the n-type quantum-well-base bipolar transistor.

8

9        Deposited on the active device layer structure is an undoped AlAs layer 182

10  which is on the order of 40-100 Å thick and a periodic layer structure formed from an

11  undoped GaAs layer 183a and an undoped AlAs layer 183b. The GaAs layer 183a and

12  AlAs layer 183b are deposited as pairs for a number of growth iterations (for example, 7

13  times as shown). Because these additional layers are formed in conjunction with the

14  active device layer structure, they are lattice matched to the underlying growth structure.

15  The thicknesses of the GaAs layers 183a of the periodic layer structure define the shift in

16  the wavelengths of the resonant cavity devices formed by the selective etching of the

17  periodic structure as described herein. Preferably, the GaAs layers 183a of the periodic

18  layer structure have uniform thicknesses to provide a uniform shift over the wavelengths

19  formed by the selective etching of the periodic structure as described herein.

20

21        It will be appreciated that AlAs layer 182 and the AlAs layers 183b of the

22  periodic structure are optional, but may be helpful. More specifically, these layers serve

23  as an etch stop when selectively etching away portions of the periodic structures to

24  thereby enable the undoped GaAs spacer layers to be removed sequentially with greater

25  accuracy and efficiency. When the AlAs layers 183b are omitted, it is possible to form

26  the GaAs spacer structure in a single growth iteration. In this case, the GaAs spacer

27  structure is selectively etched away to the depths that correspond to the vertical cavity

28  dimensions/wavelengths for the array of eight thyristor devices. This process requires

29  accurate control of the etching process, but the resulting structure is simpler and resonant

30  cavities with smaller wavelength increments can be formed.

31

1        For example, suppose that the shortest wavelength of the eight resonant cavities,

2    $\lambda_0$, is on the order of 1550 nm, and the minimum frequency interval between adjacent

3    channels, $\Delta\upsilon$, is on the order of 50 GHz. In this case, the minimum wavelength interval,

4    $\Delta\lambda$, is equal to $\Delta\upsilon\,\lambda^2/c = 2.5$ Å. This corresponds to a depth in the GaAs material of 2.5

5    Å * $n_{GaAs}$, which is on the order of 8.75 Å. The cavities are resonant at 3½ wavelengths.

6    Therefore, the thickness variation between resonant cavities will be 3.5 * 8.75 Å, which

7    is about 30.6 Å. For this thickness value, it is preferable not to use the AlAs layers 183b

8    of the periodic structure (and possibly the AlAs layer 182). Rather, the GaAs spacer

9    structure is etched in increments on the order of 30 Å in accordance with the eight

10    wavelengths of the resonant cavities, $\lambda_0$, $(\lambda_0 + \Delta\lambda)$, $(\lambda_0 + 2\,\Delta\lambda)$, $(\lambda_0 + 3\Delta\lambda)$, $(\lambda_0 + 4\Delta\lambda)$, $(\lambda_0 +$

11    $5\Delta\lambda)$, $(\lambda_0 + 6\Delta\lambda)$, and $(\lambda_0 + 7\Delta\lambda)$.

12

13        To form a resonant cavity device where light enters into and/or is emitted from

14    the device laterally (i.e., from a direction normal to the cross-section of FIG. 3), a

15    diffraction grating (for example, as described in detail in U.S. Patent 6,031,243) and top

16    dielectric mirror are formed over that portion of the periodic multilayer structure which

17    remains after selective etching of the periodic multilayer structure. For resonant cavity

18    lasing devices, the diffraction grating performs the function of diffracting light produced

19    by the resonant cavity into light propagating laterally in a waveguide which has the top

20    dielectric mirror and bottom DBR mirror as waveguide cladding layers. For resonant

21    cavity detecting devices, the diffraction grating performs the function of diffracting

22    incident light that is propagating in the lateral direction into a vertical mode, where it is

23    absorbed resonantly in the resonant cavity.

24

25        Alternatively, light may enter (and/or exit) the resonant cavity in a vertical

26    direction through an optical aperture (not shown) in the top surface (or bottom surface) of

27    the device. In this case, the diffraction grating is omitted, and the top dielectric mirror

28    and bottom DBR mirror define a resonant cavity for the vertical emission (and/or

29    absorption) of light such that the device operates as a vertical cavity surface emitting

30    laser (detector).

31

1       The optical path length between the bottom DBR mirror and top dielectric mirror

2   preferably represents an integral number of 1/2 wavelengths at the designated

3   wavelength. This optical path length is controlled by selectively etching away portions of

4   the periodic multilayer structure prior to formation of the top dielectric mirror to thereby

5   enable this condition.

6

7       FIGS. 4A and 4B in conjunction with FIGS. 5A - 5E illustrate an exemplary

8   method of fabricating the epitaxial growth structure of FIG. 3 to form an array of eight

9   multi-wavelength thyristor devices on the common substrate. The methodology begins in

10   block B2 by defining alignment marks in the structure. In block B4, the alignment marks

11   are used to perform an implant of n-type ions through implant masks 184-1, 184-2 ...

12   184-8 as shown in FIG. 5A. The implant operation is performed through the implant

13   masks 184-1...184-8 and through the periodic layer structure and P+-type ohmic contact

14   layers 165a, 165b to form the N-type implants 175 for each one of the eight thyristor

15   devices. Preferably, the N-type implants 175 are implanted to a depth near layer 162.

16

17       *In block B6, the structure is patterned and etched to form mesas at the P+-type*

18   ohmic contact layer 165b that surround the active regions 185-1, 185-2 ... 185-8 for the

19   eight thyristor devices as shown in FIG. 5A. A portion of the mesas at the P+-type ohmic

20   contact layer 165b cover the N-type implants 175.

21

22       In block B8, a metal layer 174 (preferably comprising tungsten) is deposited and

23   defined to form electrodes for the various devices. As part of block B6, metal layer 174

24   is deposited on the mesas in the P+-type ohmic contact layer 165b to form the anode

25   terminal electrodes 36-1, 36-2 ... 36-8 for the eight thyristor devices as shown in FIG. 5B.

26   A portion of the metal layer 174 covers the N-type implants 175 as best shown in FIGS.

27   6A and 6B. The metal layer 174 is also deposited on the ohmic contact layer 165b to

28   form the gate terminal electrode of each n-channel HFET device integrally formed on the

29   substrate 149 and/or to form the emitter terminal electrode for each n-type quantum-well-

30   base bipolar transistor device integrally formed on the substrate 149.

31

1          In block B10, a mask is deposited and patterned to expose a first set of active

2    regions (labeled 186) for the eight thyristor devices and protect the remaining active

3    regions (labeled 187) for the eight thyristor devices as shown in FIG. 5C. The structure is

4    then subject to an etchant that removes one period of the original seven period epitaxial

5    structure (periods of layers 183a/183b) in the exposed active areas. Preferably, a

6    chlorine-based gas mixture that includes fluorine is used as the etchant to etch down to

7    the second AlAs layer 183b (e.g., the AlAs layer 183b for the sixth period of the original

8    seven period epitaxial structure). This AlAs layer 183b is then easily dissolved in de-

9    ionized (DI) water or wet buffered hydrofluoric acid (BHF) to expose the undoped GaAs

10    layer 183a thereunder (e.g., the GaAs layer 183a for the sixth period of the original seven

11    period epitaxial structure).

12

13          In block B12, a mask is deposited and patterned to expose a second set of active

14    regions (labeled 188) for the eight thyristor devices and protect the remaining active

15    regions (labeled 189) for the eight thyristor devices as shown in FIG. 5D. The structure

16    is then subject to an etchant that removes two periods of the original seven period

17    epitaxial structure (periods of layers 183a/183b) in the exposed active areas. Preferably,

18    a chlorine-based gas mixture that includes fluorine is used as the etchant to etch down to

19    the AlAs layer 183b for the desired period of the original seven period epitaxial

20    structure). This AlAs layer 168b is then easily dissolved in de-ionized (DI) water or wet

21    buffered hydrofluoric acid (BHF) to expose the undoped GaAs layer 183a thereunder.

22

23          In block B14, a mask is deposited and patterned to expose a third set of active

24    regions (labeled 190) for the eight thyristor devices and protect the remaining active

25    regions (labeled 191) for the eight thyristor devices as shown in FIG. 5F. The structure is

26    then subject to an etchant that removes four periods of the original seven period epitaxial

27    structure (periods of layers 183a/183b) in the exposed active areas. Preferably, a

28    chlorine-based gas mixture that includes fluorine is used as the etchant to etch down to

29    the AlAs layer 183b for the desired period of the original seven period epitaxial

30    structure). This AlAs layer 168b is then easily dissolved in de-ionized (DI) water or wet

31    buffered hydrofluoric acid (BHF) to expose the undoped GaAs layer 183a thereunder. At

1    the conclusion of the operations of block B14, the height dimensions of the original seven

2    period epitaxial structure (periods of layers 183a/183b) in the active areas of the eight

3    thyristor devices have adjusted (via the selective etching operations of blocks B10, B12,

4    B14) to correspond to the eight different optical path lengths (and eight different

5    wavelengths $\lambda_1 ... \lambda_8$) for the eight thyristor laser devices of the array. For example, with

6    respect to $\lambda_1$ thyristor device, all seven periods of the original seven period epitaxial

7    structure, e.g., seven periods of layers 183a/183b, in the active area of the $\lambda_1$ thyristor

8    device are etched away during the etching operations of blocks B10, B12, B14 to form an

9    optical path length that corresponds to $\lambda_1$. With respect to the $\lambda_3$ thyristor device, five

10   periods of the original seven period epitaxial structure, e.g., five periods of layers

11   183a/183b, in the active area of the $\lambda_3$ thyristor device are etched away during the etching

12   operations of blocks B10 and B14 to form an optical path length that corresponds to $\lambda_3$.

13   With respect to the $\lambda_8$ thyristor device, zero periods of the original seven period epitaxial

14   structure, zero periods of layers 183a/183b, in the active area of the $\lambda_8$ thyristor device

15   are etched away during the etching operations of blocks B10, B12 and B14 to form an

16   optical path length that corresponds to $\lambda_8$.

17

18

19         In block B16, the resulting structure of block B14 is patterned and etched to

20   expose regions at (or near) layer 163c. An implant of n-type ions is implanted into the

21   exposed regions to form N+-type implants 170, which are used to contact to the n-type

22   QW structure 24 for the eight thyristor devices of the array (as best shown in FIGS. 6A

23   and 6B). The N+-type implants 170 are also used to form source and drain channel

24   contacts in each n-channel HFET device integrally formed on the substrate 149 and/or to

25   form a base contact in each n-type quantum-well-base bipolar transistor device integrally

26   formed on the substrate 149. Advantageously, the N+-type implants 170 are self-aligned

27   by the anode terminal electrodes formed on the mesas above the implants 170 as shown

28   in FIGS. 6A and 6B.

29

30         In block B18, the resultant structure of block B16 is subject to an etching

31   operation that exposes regions preferably at or near layer 158. An implant of p-type ions

1    is implanted into the exposed regions to form the P+-type implants 171, which are used

2    to contact the p-type QW structure 20 (layers 155-158) for the eight thyristor devices (as

3    best shown in FIGS. 6A and 6B). The P+-type implants 171 are also used to form the

4    collector contact for each n-channel HFET devices integrally formed on the substrate

5    149, to form the source and drain channel contacts for each p-channel HFET device

6    integrally formed on the substrate 149, to form the base contact for each p-type quantum-

7    well-base bipolar transistor device integrally formed on the substrate 149, and/or to form

8    the collector contact for each n-type quantum-well-base bipolar transistor device

9    integrally formed on the substrate 149.

10

11       In block B20, the resultant structure of block B18 is subject to a patterning and

12   etching operation that exposes regions of ohmic contact layer 153. The exposed regions

13   of layer 153 are used to form a low resistance contact to the cathode terminal electrodes

14   40a, 40b for the eight thyristor devices as shown in FIG. 6A and 6B. The exposed

15   regions of layer 153 are also used to form gate electrode for each p-channel HFET device

16   integrally formed on the substrate 149, and/or to form the emitter electrode for each p-

17   type quantum-well-base bipolar transistor device integrally formed on the substrate 149.

18

19       In block B22, the structure is subjected to a rapid thermal anneal (RTA) of the

20   order of 950°C to activate all implants.

21

22       In block B24, the devices are isolated from one another by an etch operation

23   down to the semi-insulating substrate 149, which includes an etch through the mirror

24   pairs 151/152 of AlAs/GaAs.

25

26       In block B26, the structure is oxidized in a steam ambient to convert layers 151 to

27   AlO, which form the bottom DBR mirror 12. During this oxidation step, the exposed

28   sidewalls of the etched AlGaAs layers are passivated by the formation of very thin layers

29   of oxide.

30

1    In block B28, layers 179/180 are deposited to form a top dielectric mirror.

2    Preferably, the layers 179/80 comprise $SiO_2$ and a high refractive index material such as

3    GaAs, Si, or GaN. In addition, a diffraction grating may be formed in conjunction with

4    the formation of the top dielectric mirror as described in detail in U.S. Patent 6,031,243.

5

6    Finally, in block B30, metal layers 176, 178 and 181 are deposited and defined

7    (preferably via lift off). Metal layer 176 (which preferably comprises an n-type Au alloy

8    metal such as AuGe/Ni/Au) is deposited on the N+ type implants 170 to form the N-

9    channel injector terminal electrodes 38a, 38b of the thyristor devices as shown in FIGS.

10   6A and 6B. Metal layer 178 (which preferably comprises a p-type Au metal alloy such as

11   AuZn/Cr/Au) is deposited on the P+ type implants 171 to form the p-channel injector

12   terminal electrodes 38c, 38d of the thyristor devices as shown. Metal layer 181 (which

13   preferably comprises an n-type Au alloy metal such as AuGe/Ni/Au) is deposited on the

14   mesas at the N+ layer 153 to form the cathode terminal electrodes 40A, 40B of the

15   thyristor devices as shown. Metal layer 176 may also be used to form the

16   source terminal electrode and drain terminal electrode of each n-channel HFET device

17   integrally formed on the substrate 149, to form the base terminal electrode of each n-type

18   quantum-well-base bipolar transistor device integrally formed on the substrate 149,

19   and/or to form the collector terminal electrode of each p-type quantum-well-base bipolar

20   transistor device integrally formed on the substrate 149. Metal layer 178 may also be

21   used to form the source terminal electrode and drain terminal electrode of each p-channel

22   HFET device integrally formed on the substrate 149, to form the base terminal electrode

23   of each p-type quantum-well-base bipolar transistor device integrally formed on the

24   substrate 149, and/or to form the collector terminal electrode of each n-type quantum-

25   well-base bipolar transistor device integrally formed on the substrate 149. Metal layer

26   181 may also be used to form the gate terminal electrodes of each p-channel HFET

27   device integrally formed on the substrate 149, and/or to form the emitter terminal

28   electrode of each p-type quantum-well-base bipolar transistor device integrally formed on

29   the substrate 149.

30

1     FIG. 6A is a cross-section view illustrating the thyristor device of the array which

2     corresponds to a wavelength $\lambda_4$ (of the eight different wavelengths $\lambda_1$ ... $\lambda_8$ of the thyristor

3     devices of the array). This device has three periods (183-1, 183-2, and 183-3) remaining

4     from the original seven period structure as a result of the selective etching operations of

5     blocks B10, B12 and B14 (Fig. 4A).

6

7     FIG. 6B is a cross-section view illustrating the thyristor device of the array which

8     corresponds to a wavelength $\lambda_7$ (of the eight different wavelengths $\lambda_1$ ... $\lambda_8$ of the thyristor

9     devices of the array). Note that this device has six periods (183-1 ... 183-6) remaining

10    from the original seven period structure as a result of the selective etching operations of

11    blocks B10, B12 and B14 (Fig. 4A).

12

13    Advantageously, and as previously described, the selective etching operations of

14    blocks B10, B12 and B14 utilize three masks to define the eight different wavelengths $\lambda_1$

15    ... $\lambda_8$ of the thyristor devices of the array. This minimizes the cost of manufacturing the

16    array. It should be appreciated that the 7-period epitaxial growth structure and associated

17    3-mask etching operation may be readily expanded to provide for a larger number of

18    wavelengths/devices. For example, a 15-period epitaxial growth structure and associated

19    4-mask etching operation may be used to provide for 16 different wavelengths/devices,

20    while a 31-period epitaxial growth structure and associated 5-mask etching operation

21    may be used to provide for 32 different wavelengths/devices. Note that this may be

22    generalized by the following relationship: a $(2^X-1)$ period epitaxial growth structure and

23    associated $X$-mask etching operation may be used to provide for $2^X$ different

24    wavelengths/devices, where $X$ is an integer greater than 1.

25

26    FIG. 7 illustrates the operational characteristics of the thyristor devices of the

27    thyristor array described herein. The thyristor switches from a non-conducting/OFF state

28    (where the current $I$ through the device is substantially zero) to a conducting/ON state

29    (where the current $I$ is substantially greater than zero) when: i) the anode terminals 36a,

30    36b are forward biased (e.g. biased positively) with respect to the cathode terminals 40a,

31    40b; and ii) the voltage between injector electrode(s) and anode electrode is biased for a

1     period long enough to produce a charge in the N-type modulation doped QW

2     heterostructure 24 (and/or produce a charge in the P-type modulation doped QW

3     heterostructure 20) that is greater than the critical switching charge $Q_{CR}$, which is that

4     charge that reduces the forward switching voltage such that no off state bias point exists.

5

6     The thyristor device can also be switched into the ON state with optical energy.

7     More specifically, the thyristor device is switched from a non-conducting/OFF state

8     (where the current $I$ through the device is substantially zero) to a conducting/ON state

9     (where the current $I$ is substantially greater than zero) when: i) the anode terminals 36a,

10     36b are forward biased (e.g. biased positively) with respect to the cathode terminals 40a,

11     40b; and ii) optical energy is introduced into the quantum well structure(s) of the device

12     that is sufficient to produce the critical switching charge $Q_{CR}$.

13

14     As an optoelectronic component, the thyristor is multifunctional. If the current $I$

15     in the conducting/ON state is above the threshold for lasing ($I_L$), then laser emission will

16     occur. This is the operation of a semiconductor laser. It can be activated with electrical

17     signals supplied to the injector terminal(s) of the device as well as optical energy injected

18     into the device. This configuration is preferably achieved by applying a forward bias

19     between the anode and cathode terminals that is less than the maximum forward

20     switching voltage of the device. In addition, the injector terminal(s) of the device are

21     biased with respect to the anode terminal through a current source that generates a bias

22     current $I_{BIAS}$. When an input electrical pulse is supplied to the injector terminal(s) of the

23     device (or an optical pulse is supplied to device), in the event that the supplied pulse has

24     sufficient energy to produce current in excess of the bias current $I_{BIAS}$ drawing on the

25     injector terminal(s) and such current produces the critical switching charge $Q_{CR}$, the

26     thyristor will switch to its conducting/ON state. In the ON state, if the current $I$ is above

27     the threshold for lasing ($I_L$), then laser emission will occur to produce an output optical

28     pulse that is emitted from the device. When the input pulse is reduced, the thyristor will

29     switch to the OFF state because the bias current $I_{BIAS}$ provided by the current source to

30     the injector terminal(s) drains the QW channel(s) of charge, which causes the channel

31     charge to fall below the holding charge $Q_H$. In the OFF state, the current $I$ through the

1    device is near zero, thereby terminating the corresponding output optical pulse emitted

2    from the device.  In this manner, the thyristor device can be configured to operate as a

3    vertical cavity laser that produces an output optical pulse (in response to an input

4    electrical/optical pulse).

5

6

7            The thyristor device can be configured to operate as an optical detector that

8    detects an input optical pulse and produces a corresponding output electrical pulse (or

9    output optical pulse) in response to a detected input optical pulse.  In this configuration,

10   the thyristor device is in the non-conducting/OFF state and functions as an optical

11   detector when light is admitted into the cavity in the sense that when sufficient electron-

12   hole pairs have been generated to produce the critical switching charge $Q_{CR}$, the thyristor

13   will switch to its ON state.  In the ON state, the device produces an electrical output pulse

14   (and possibly an output optical pulse).  This configuration is achieved by applying a

15   forward bias between the anode and cathode terminals that is less than the maximum

16   forward switching voltage of the device.  In addition, the injector terminal(s) of the

17   device are biased with respect to the anode terminal through a current source that

18   generates a bias current $I_{BIAS}$.  When an input optical pulse is incident on the thyristor, in

19   the event that the incident light has sufficient intensity to produce photocurrent in excess

20   of the bias current $I_{BIAS}$ drawing on the injector terminal(s) and such photocurrent

21   produces the critical switching charge $Q_{CR}$, the thyristor will switch to its conducting/ON

22   state.  In the ON state, the current $I$ through the device produces a corresponding output

23   electrical pulse at the cathode terminal (and/or at the anode terminal) of the device.

24   When the incident light is reduced, the thyristor will switch to the OFF state because the

25   bias current $I_{BIAS}$ provided by the current source to the injector terminal(s) drains the QW

26   channel(s) of charge, which causes the channel charge to fall below the holding charge

27   $Q_H$.  In the OFF state, the current $I$ through the device is near zero, thereby terminating the

28   corresponding output pulse produced at the cathode terminal (and/or the anode terminal)

29   of the device.  When the thyristor device is configured as a vertical cavity detector, the

30   current through the device in the ON state may be set above the threshold for lasing.  This

31   configuration is referred to herein as an optical detector/emitter.  It operates as a vertical

1 cavity laser that produces an output optical pulse in response to the detection of a

2 corresponding input optical pulse.

3

4 In addition, the thyristor device can be configured to operate as various other

5 optoelectronic components including a PIN detector, digital optical modulator, analog

6 optical modulator, and optical amplifier as described below.

7

8 A PIN detector generates an electrical signal proportional to the optical signal

9 incident thereon. To configure the thyristor device as a PIN detector, the cathode

10 terminals 40a, 40b float electrically and a reverse bias is applied between the n-channel

11 injector terminals 38a, 38b and the anode terminals 36a, 36b. Such a configuration

12 creates a reverse-bias PIN junction that generates an electrical signal (photocurrent)

13 proportional to the optical signal incident to the vertical cavity.

14

15 A digital optical modulator operates in one of two distinct optical states in

16 modulating an input optical signal. In optical state 1, there is no loss to input optical

17 signal via absorption. In optical state 2, all of the input optical signal is absorbed. To

18 configure the thyristor device as a digital optical modulator, an optical path is provided

19 through the device either vertically or in the waveguide mode, and an input signal is

20 applied to the n-channel injector terminal 38a, 38b with respect to the anode terminals

21 36a, 36b.

22

23 When the input signal produces a forward bias between the n-channel injector

24 terminals 38a, 38b and the anode terminals 36a, 36b sufficient to produce charge in the

25 N-type modulation doped QW heterostructure 24 greater than the critical switching

26 charge $Q_{CR}$, the thyristor operates in its conducting/ON state. The device is biased such

27 that the current $I$ through the device in the ON state is substantially below the threshold

28 for lasing (preferably about one-third of the lasing threshold current). In this

29 configuration, in the ON state, the device operates in optical state 1 whereby there is no

30 loss to input optical signal via absorption.

31

1            When the input signal produces a reverse bias between the n-channel injector

2    terminals 38a, 38b and the anode terminals 36a, 36b which draws current from the anode

3    terminals sufficient to decrease the charge in the N-type modulation doped QW

4    heterostructure 24 below the hold charge $Q_H$, the thyristor operates in its non-

5    conducting/OFF state. In the OFF state, the device operates in optical state 2 whereby all

6    of the input optical signal is absorbed.

7

8            An analog optical modulator modulates an input optical signal linearly over a

9    range of modulation values. To configure the thyristor device structure as an analog

10    optical modulator, the cathode terminals 40a, 40b float electrically and the thyristor

11    function is deactivated. An optical path is provided through the device either vertically

12    or in the waveguide mode, and an input signal is applied to the anode terminals 36a, 36b

13    with respect to the n-channel injector terminals 38a, 38b such that the anode terminals

14    36a, 36b are biased positively with respect to the n-channel injector terminals 38a, 38b.

15    In this configuration, the voltage at the anode terminals 36a, 36b is varied over a range of

16    voltage levels where absorption of the device varies linearly. The top of the voltage

17    range (where minimum absorption occurs) is defined by the operation point where

18    conduction occurs from the anode terminals 36a, 36b to the injector terminals 38a, 38b.

19

20            An optical amplifier amplifies an input optical signal to produce a corresponding

21    output optical signal with an increased intensity level. To configure the thyristor device

22    as an optical amplifier, the diffraction grating is omitted and an input optical signal is

23    injected into the optically-active region of the device. A forward bias is applied between

24    the anode and cathode terminals through a load resistance that sets the current $I$ through

25    the device in the ON state at a point substantially below the lasing threshold $I_L$. In this

26    configuration, in the ON state, the device amplifies the input optical signal to produce a

27    corresponding output optical signal with an increased intensity level. The optical

28    amplifier may be switched into and out of the ON state by applying forward and reverse

29    biases to the n-channel injector terminals 38a, 38b with respect to the anode terminals

30    36a, 36b as described above. The gain of the optical amplifier in the ON state and thus

1   the output signal intensity level may be changed by adjusting the current $I$ in the ON

2   state.

3

4        In this manner, the array of thyristor devices as described herein may be used to

5   realize an array of devices that provide a variety of optoelectronic functions. For

6   example, to realize an array of thyristor-based lasers that emit light at different

7   wavelengths (e.g., for wavelength-division-multiplexing applications), the array of

8   thyristor devices is formed such that the vertical dimensions of the resonant cavities for

9   the thyristor devices corresponds to the desired wavelengths. In another example, to

10  realize an array of thyristor-based detectors that detect light at different wavelengths

11  (e.g., for wavelength-division-multiplexing applications), the array of thyristor devices is

12  formed such that the vertical dimensions of the resonant cavities for the thyristor devices

13  corresponds to the desired wavelengths. Incident light (which includes light components

14  at the different wavelengths) is guided to the array of thyristor devices. Each thyristor

15  device is biased such that the incident light component of a particular wavelength (e.g.,

16  an ON light pulse at the particular wavelength) will be resonantly absorbed and switch

17  the device into its ON state, which produces a corresponding output electrical signal. In

18  the ON state, the device may produce a corresponding output optical signal via lasing

19  action if the device is biased such that the current I in the ON state is above the threshold

20  for lasing $I_L$. Similarly, the array of multi-wavelength thyristor devices can be used to

21  realize an array of PIN detector devices that detect incident light at different wavelengths,

22  an array of optical modulator devices that modulate incident light at different

23  wavelengths, and an array of optical amplifier devices that amplify incident light at

24  different wavelengths.

25

26        In addition, the multilayer structures of FIG. 1 and 3 may be used to realize

27  various transistor devices (such as n-channel HFETs, p-channel HFETs, p-type quantum-

28  well-base bipolar transistors, n-type quantum-well-base bipolar transistors), waveguide

29  devices, and other optoelectronic devices (such as optical interconnects). The details of

30  such devices are described in the previously incorporated patent applications. Thus, the

31  multi-wavelength thyristor array as described herein is well suited for monolithic

1   integration with a broad range of electronic devices and optoelectronic devices (such as

2   n-channel HFETs, p-channel HFETs, p-type quantum-well-base bipolar transistors, n-

3   type quantum-well-base bipolar transistors, waveguide devices, and other optoelectronic

4   devices such as optical interconnects).

5

6   There have been described and illustrated herein several embodiments of a multi-

7   wavelength thyristor array employing modulation doped quantum well structures and a

8   method of fabricating such multi-wavelength thyristor arrays. While particular

9   embodiments of the invention have been described, it is not intended that the invention be

10  limited thereto, as it is intended that the invention be as broad in scope as the art will

11  allow and that the specification be read likewise. Thus, while particular layers have been

12  described with particular thicknesses and with particular types and strengths of dopings,

13  it will be appreciated that certain transition layers could be removed and/or additional

14  layers and/or sublayers could be utilized, and further that the layers could have different

15  thicknesses and be differently doped. Also, while particular layers have been described

16  with reference to their percentage content of certain constituents, it will be appreciated

17  that the layers could utilize the same constituents with different percentages, or other

18  constituents. Additionally, while particular formation and metallization techniques have

19  been described, it will be appreciated that the described structures can be formed in other

20  manners, and other metals used to form terminals. Further, while particular arrangements

21  of thyristor devices, optical emitters, detectors, modulators, amplifiers, etc. formed from

22  the described semiconductor structure, it will be appreciated that other devices and

23  circuits can be made from the provided structure and components. It will therefore be

24  appreciated by those skilled in the art that yet other modifications could be made to the

25  provided invention without deviating therefrom.